

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

85-103881/17

C04E34

URAL= 04.05.83

C(5-A1A, 12-M11)E(33-B, 35-U) 2

101

URALS HALURGY RES

*SU 1117-281-A

04.05.83-SU-586159 (07.10.84) C01d-03/22 C05d-01/02

Mfr. of granulated potassium chloride - by treating obtd. granules with ferric sulphate and drying before storage

CR5-045333

Prepn. of granulated KCl. Includes granulating fine-grain prod. and treating the granules with Fe (III) salt. The caking of the prod. is decreased, and its moisture resistance increased by using 5-10% Fe₂(SO₄)₃ soln. at 0.3-0.5kg per t as the Fe (III) salt, with subsequent drying of the obtd. prod. at 80-110 deg.C.

ADVANTAGE - The caking of KCl is decreased 4-5 fold and its resistance to moisture is increased 2.5-3 fold. (2pp Dwg.No. 0/0)

EXAMPLE

The initial fine-grain KCl was granulated by pressing it at 8 MPa and 110-130 deg. C. The obtd. material was granulated, the granules were classified, retaining greater than 4mm particles, these were then treated with 5% soln. of Fe₂(SO₄)₃ at 0.3kg per t and dried at 80 deg. C. Bul.37/7.10.84.